

Appendix: Drill Results

Table 1: SCC Drill Results

HOLE-ID	From (m)	Core Length (m)	Estimated True Width (%)		Au (g/t)	CN Rec (%)	Au GXM	Oxide Domain	Including 0.5g/t Au COG	Including 1g/t Au COG	Including 2g/t Au COG	Including 10g/t Au HG	Method
BW25-01	96.0	6.1	5.9	96.2%	0.24	98.0	1.45	Oxide					FA
BW25-01	108.2	18.3	17.7	96.5%	0.62	101.7	11.42	Oxide	9.1m @ 1.08g/t Au & 101.3% CN Rec	7.6m @ 1.1g/t Au & 100% CN Rec			FA
BW25-02	70.1	21.3	20.0	93.7%	0.74	14.8	15.76	Sulphide		1.5m @ 1.16g/t Au & 18.2% CN Rec	1.5m @ 1.08g/t Au & 15.8% CN Rec		FA
BW25-04	129.5	1.5	1.5	99.7%	0.93	11.8	1.42	Sulphide					FA
BW25-04	144.8	3.0	3.0	99.4%	0.24	87.5	0.75	Oxide					FA
BW25-05	16.8	1.5	1.1	70.5%	0.60	26.7	0.91	Sulphide					FA
BW25-05	18.3	1.5	1.1	70.5%	0.20	96.4	0.30	Oxide					FA
BW25-05	22.9	10.7	7.5	70.5%	1.61	10.5	17.13	Sulphide		4.6m @ 3.09g/t Au & 3.4% CN Rec	1.5m @ 7.61g/t Au & 2.2% CN Rec		FA
BW25-05	99.1	1.5	1.1	73.6%	0.53	7.5	0.81	Sulphide					FA
BW25-05	123.4	3.0	2.3	74.3%	2.58	16.7	7.85	Sulphide		3m @ 2.58g/t Au & 16.7% CN Rec	3m @ 2.58g/t Au & 16.7% CN Rec		FA
BW25-05	207.3	13.7	13.4	97.9%	0.33	60.1	4.59	Oxide	3m @ 0.84g/t Au & 87.5% CN Rec				FA
BW25-05	236.2	1.5	1.5	97.8%	0.21	75.1	0.32	Oxide					FA
BW25-05	243.8	1.5	1.5	97.7%	0.17	75.1	0.26	Oxide					FA
BW25-06	68.6	9.1	8.4	91.7%	0.23	52.2	2.14	Oxide					FA
BW25-06	91.4	1.5	1.4	90.9%	0.29	82.5	0.44	Oxide					FA
BW25-06	114.3	1.5	1.5	99.5%	0.18	91.4	0.27	Oxide					FA
BW25-06	149.4	4.6	4.6	99.6%	0.40	102.1	1.84	Oxide	1.5m @ 0.53g/t Au & 98.9% CN Rec				FA
BW25-06	160.0	3.0	3.0	99.6%	0.45	96.9	1.37	Oxide	1.5m @ 0.68g/t Au & 96% CN Rec				FA
BW25-06	170.7	13.7	13.7	99.6%	0.44	78.7	5.99	Oxide	4.6m @ 0.89g/t Au & 98.6% CN Rec	1.5m @ 1.25g/t Au & 83.5% CN Rec			FA
BW25-07	62.5	1.5	1.4	89.2%	0.19	63.2	0.29	Oxide					FA
BW25-07	67.1	1.5	1.4	89.2%	0.59	44.4	0.89	Oxide	1.5m @ 0.58g/t Au & 44.4% CN Rec				FA
BW25-07	70.1	1.5	1.4	89.2%	0.59	17.1	0.89	Sulphide					FA
BW25-07	82.3	1.5	1.4	95.1%	0.18	111.1	0.27	Oxide					FA
BW25-07	89.9	13.7	13.1	95.3%	0.24	113.0	3.27	Oxide					FA
BW25-07	111.3	4.6	4.4	95.6%	0.20	114.1	0.94	Oxide					FA
BW25-08	105.2	3.0	2.9	95.5%	0.66	24.5	2.01	Sulphide					FA
BW25-08	129.5	22.9	21.9	95.8%	0.51	78.1	11.60	Oxide	13.7m @ 0.65g/t Au & 75.7% CN Rec	1.5m @ 1.4g/t Au & 65.5% CN Rec			FA
BW25-08	195.1	3.0	2.9	96.0%	0.96	90.0	2.92	Oxide	3m @ 0.96g/t Au & 90% CN Rec	1.5m @ 1.16g/t Au & 94.4% CN Rec			FA
BW25-09	99.1	4.6	3.3	71.8%	1.56	95.7	7.12	Oxide	3m @ 2.13g/t Au & 96.2% CN Rec	1.5m @ 3.7g/t Au & 104.3% CN Rec	1.5m @ 3.7g/t Au & 104.3% CN Rec		FA
BW25-09	111.3	1.5	1.1	71.5%	0.19	80.2	0.28	Oxide					FA
BW25-09	134.1	13.7	9.8	71.2%	0.65	75.3	8.97	Oxide	3m @ 2.18g/t Au & 55% CN Rec	3m @ 2.18g/t Au & 55% CN Rec	3m @ 2.18g/t Au & 55% CN Rec		FA
BW25-11	106.7	3.0	2.3	76.9%	0.44	94.4	1.33	Oxide	1.5m @ 0.56g/t Au & 97.1% CN Rec				FA
BW25-11	120.4	3.0	2.3	76.3%	0.19	93.2	0.59	Oxide					FA
BW25-11	163.1	6.1	4.6	75.3%	0.36	100.9	2.21	Oxide	1.5m @ 0.55g/t Au & 102% CN Rec				FA
BW25-14	22.9	19.8	10.9	55.0%	0.23	74.4	4.59	Oxide	1.5m @ 0.6g/t Au & 90.9% CN Rec				FA
DS25-02	164.6	3.0	2.1	68.2%	0.28	104.7	0.85	Oxide					FA
DS25-02	219.5	1.5	1.0	68.6%	0.23	82.6	0.35	Oxide					FA
DS25-02	249.9	10.7	7.4	69.5%	1.67	9.0	17.77	Sulphide	9.1m @ 1.83g/t Au & 10.1% CN Rec	3m @ 3.46g/t Au & 11.6% CN Rec			FA
DS25-03	157.0	1.5	1.1	70.3%	0.20	75.0	0.30	Oxide					FA

DS25-03	167.9	22.6	15.9	70.3%	5.65	93.4	127.50	Oxide	22.6m @ 5.65g/t Au & 93.4% CN Rec	17.4m @ 7.14g/t Au & 91.9% CN Rec	17.4m @ 7.14g/t Au & 91.9% CN Rec	5m @ 15.1g/t Au & 87.6% CN Rec	FA
DSC25-03	328.7	1.6	1.2	78.5%	0.64	2.3	1.02	Sulphide					FA
DSC25-04	260.8	3.2	2.3	73.3%	0.93	50.8	2.96	Oxide	3.2m @ 0.93g/t Au & 50.8% CN Rec	1.8m @ 1.11g/t Au & 55.9% CN Rec			FA
DSC25-04	264.0	4.6	3.3	73.3%	0.67	5.0	3.07	Sulphide					FA
DSC25-05	194.5	12.0	8.4	69.9%	0.18	100.9	2.18	Oxide	1.5m @ 0.54g/t Au & 109.7% CN Rec				FA
DSC25-05	225.1	1.0	0.7	69.6%	0.19	82.9	0.19	Oxide					FA
DSC25-05	228.8	2.7	1.9	69.3%	1.64	13.5	4.39	Sulphide		2.7m @ 1.64g/t Au & 13.5% CN Rec			FA
DSC25-05	235.7	1.1	0.8	69.3%	0.86	42.0	0.97	Oxide	1.1m @ 0.86g/t Au & 42% CN Rec				FA
DSC25-05	238.0	8.0	5.5	69.3%	1.91	16.4	15.20	Sulphide		6.4m @ 2.15g/t Au & 14% CN Rec	3.7m @ 2.85g/t Au & 12.4% CN Rec		FA
DSC25-05	255.1	1.9	1.3	69.0%	2.89	3.5	5.46	Sulphide		1.9m @ 2.89g/t Au & 3.5% CN Rec	1.9m @ 2.89g/t Au & 3.5% CN Rec		FA
JW25-01	0.0	1.5	1.2	79.6%	0.18	87.4	0.28	Oxide					FA
JW25-01	99.1	3.0	2.4	77.8%	0.33	110.4	0.99	Oxide					FA
JW25-02	12.2	1.5	0.7	43.2%	0.78	59.1	1.19	Oxide	1.5m @ 0.78g/t Au & 59.1% CN Rec				FA
JW25-02	16.8	4.6	2.0	43.3%	0.90	32.1	4.12	Sulphide		1.5m @ 1.2g/t Au & 33.2% CN Rec			FA
JW25-02	21.3	13.7	5.9	43.3%	0.73	44.8	9.95	Oxide	3m @ 0.94g/t Au & 42.2% CN Rec 4.6m @ 0.98g/t Au & 50.2% CN Rec	1.5m @ 1.23g/t Au & 40% CN Rec 3m @ 1.16g/t Au & 50.3% CN Rec			FA
JW25-02	39.6	1.5	0.7	43.5%	0.24	41.0	0.37	Oxide					FA
JW25-02	106.7	18.3	8.4	45.7%	0.30	86.2	5.42	Oxide	1.5m @ 0.54g/t Au & 93.9% CN Rec				FA
JW25-02	131.1	10.7	4.9	45.8%	0.26	76.8	2.78	Oxide					FA
JW25-02	170.7	1.5	0.7	45.7%	0.20	94.5	0.31	Oxide					FA
JW25-02	175.3	6.1	2.8	45.7%	0.19	82.6	1.14	Oxide					FA
JW25-02	204.2	1.5	0.7	45.7%	0.21	48.5	0.31	Oxide					FA
JW25-02	208.8	1.5	0.7	45.7%	0.28	40.0	0.42	Oxide					FA
JW25-03	10.7	1.5	1.4	94.0%	0.18	73.4	0.27	Oxide					FA
JW25-03	33.5	1.5	1.4	93.9%	0.18	61.8	0.27	Oxide					FA
JW25-03	50.3	6.1	5.7	94.1%	0.19	106.9	1.14	Oxide					FA
JW25-03	67.1	3.0	2.9	94.5%	0.26	106.1	0.79	Oxide					FA
JW25-04	59.4	12.2	9.2	75.5%	0.74	18.2	9.08	Sulphide		3m @ 1.08g/t Au & 15.2% CN Rec			FA
JW25-04	109.7	18.3	13.7	75.2%	0.34	81.5	6.18	Oxide	1.5m @ 0.7g/t Au & 86.2% CN Rec 1.5m @ 0.54g/t Au & 96.8% CN Rec				FA
JW25-04	135.6	4.6	3.4	75.1%	0.20	77.0	0.94	Oxide					FA
JW25-04	146.3	9.1	6.9	75.1%	0.21	76.8	1.89	Oxide					FA
JW25-05	24.4	6.1	4.4	72.8%	0.54	73.7	3.28	Oxide	4.6m @ 0.58g/t Au & 61.7% CN Rec				FA
JW25-05	35.1	3.0	2.2	73.5%	0.78	29.2	2.38	Sulphide					FA
JW25-05	50.3	4.6	3.4	74.1%	0.75	23.1	3.44	Sulphide					FA
JW25-05	76.2	4.6	3.4	75.5%	1.06	11.1	4.85	Sulphide		1.5m @ 1.36g/t Au & 11.7% CN Rec			FA
JW25-05	108.2	13.7	10.5	76.2%	0.25	100.6	3.43	Oxide					FA
JW25-05	143.3	1.5	1.1	74.8%	0.19	86.0	0.28	Oxide					FA
JW25-06	10.7	1.5	1.2	76.5%	0.20	91.8	0.30	Oxide					FA
JW25-06	16.8	1.5	1.2	76.1%	0.19	86.5	0.28	Oxide					FA
JW25-06	22.9	1.5	1.2	76.1%	0.18	68.6	0.27	Oxide					FA
JW25-06	29.0	1.5	1.2	76.1%	0.20	96.9	0.30	Oxide					FA
JW25-06	36.6	21.3	16.2	75.8%	0.22	101.6	4.79	Oxide					FA
JW25-06	65.5	25.9	19.3	74.6%	0.25	93.6	6.43	Oxide	3m @ 0.66g/t Au & 97.7% CN Rec				FA
JW25-06	97.5	1.5	1.1	74.3%	0.26	97.3	0.39	Oxide					FA
JW25-06	106.7	38.1	28.0	73.5%	0.32	74.1	12.00	Oxide	9.1m @ 0.62g/t Au & 77.7% CN Rec	1.5m @ 1.52g/t Au & 59.9% CN Rec			FA
JW25-07	64.0	3.0	2.3	75.9%	0.53	9.4	1.61	Sulphide					FA
JW25-07	140.2	3.0	2.2	72.0%	0.20	69.4	0.59	Oxide					FA

JW25-07	155.4	3.0	2.2	71.0%	0.19	67.6	0.57	Oxide											FA
JW25-07	167.6	4.6	3.2	70.8%	0.22	89.4	1.03	Oxide											FA
JW25-07	179.8	3.0	2.2	70.8%	0.20	73.6	0.60	Oxide											FA
JW25-08	96.0	1.5	0.9	61.7%	1.24	18.6	1.88	Sulphide					1.5m @ 1.24g/t Au & 18.6% CN Rec						FA
JW25-09	54.9	1.5	1.5	99.6%	0.17	40.9	0.26	Oxide											FA
JW25-09	57.9	1.5	1.5	99.6%	0.21	53.4	0.31	Oxide											FA
JW25-10	48.8	19.8	14.3	72.2%	0.25	62.0	4.99	Oxide											FA
JW25-11	51.8	1.5	1.5	99.4%	0.19	90.9	0.28	Oxide											FA
JW25-11	68.6	1.5	1.5	99.5%	0.19	84.7	0.29	Oxide											FA
JW25-12	19.8	3.0	3.0	99.8%	0.40	107.3	1.22	Oxide											FA
JW25-12	39.6	3.0	3.0	99.9%	0.21	88.1	0.64	Oxide											FA
JW25-12	59.4	1.5	1.5	100.0%	0.21	86.1	0.32	Oxide											FA
JW25-13	24.4	3.0	2.1	68.1%	0.25	58.4	0.76	Oxide											FA
JW25-13	32.0	1.5	1.0	67.6%	0.18	82.9	0.28	Oxide											FA
JW25-13	39.6	15.2	10.2	67.0%	0.18	83.4	2.69	Oxide											FA
JW25-13	70.1	1.5	1.0	66.7%	0.28	77.5	0.43	Oxide											FA
PAL25-01A	152.4	1.5			0.19	91.9	0.28	Oxide											FA
PAL25-04	25.9	3.0			0.31	107.8	0.94	Oxide											FA
PR25-01	204.2	21.3	21.2	99.4%	0.75	97.8	15.94	Oxide	18.3m @ 0.83g/t Au & 98.2% CN Rec			6.1m @ 1.21g/t Au & 98.9% CN Rec							FA
PR25-02	248.4	1.5	1.5	99.6%	0.55	29.3	0.83	Sulphide											FA
PR25-02	249.9	32.0	31.9	99.8%	0.94	72.0	30.03	Oxide	30.5m @ 0.97g/t Au & 73.3% CN Rec			10.7m @ 1.49g/t Au & 84.2% CN Rec			1.5m @ 2.61g/t Au & 87% CN Rec			FA	
PR25-04	260.6	15.2	15.1	99.3%	0.49	72.3	7.45	Oxide	12.2m @ 0.54g/t Au & 78.8% CN Rec										FA
PR25-04	283.5	3.0	3.0	99.2%	0.56	8.8	1.71	Sulphide											FA
PR25-04	309.4	1.5	1.5	99.1%	0.51	9.9	0.77	Sulphide											FA
PR25-05	221.0	67.1	65.2	97.2%	1.16	80.7	77.55	Oxide	61m @ 1.25g/t Au & 80.5% CN Rec			36.6m @ 1.68g/t Au & 79.7% CN Rec 3m @ 1.57g/t Au & 83.9% CN Rec			3m @ 2.66g/t Au & 91.2% CN Rec 3m @ 2.72g/t Au & 77.4% CN Rec			Photon	
PR25-06	202.7	6.1	6.1	99.8%	0.47	97.4	2.86	Oxide	3m @ 0.68g/t Au & 94.8% CN Rec										FA
PR25-09	44.2	24.4			1.08	96.3	26.42	Oxide	16.8m @ 1.43g/t Au & 97.1% CN Rec			10.7m @ 1.86g/t Au & 100.3% CN Rec			3m @ 2.7g/t Au & 100.3% CN Rec			FA	
PR25-09	76.2	1.5			0.64	92.8	0.97	Oxide	1.5m @ 0.64g/t Au & 92.8% CN Rec										FA
PR25-09	190.5	1.5			0.21	93.9	0.32	Oxide											FA
RBN25-01	25.9	1.5			0.21	111.7	0.31	Oxide											FA
RBN25-02	117.3	3.0			0.88	108.6	2.69	Oxide	1.5m @ 1.46g/t Au & 108.9% CN Rec			1.5m @ 1.46g/t Au & 108.9% CN Rec							FA
RBN25-03	70.1	10.7			0.35	102.3	3.75	Oxide	1.5m @ 0.53g/t Au & 106.7% CN Rec										FA
RR25-01	18.3	3.0	3.0	98.6%	0.31	100.6	0.93	Oxide											FA
RR25-01	211.8	6.1	6.0	99.2%	0.26	92.3	1.56	Oxide											FA
RR25-01	237.7	3.0	3.0	99.2%	0.22	79.9	0.67	Oxide											FA
RR25-02	1.5	10.7	8.7	81.2%	0.18	67.7	1.95	Oxide											FA
RR25-03	24.4	1.5	1.5	99.6%	0.21	94.3	0.32	Oxide											FA
RR25-03	230.1	16.8	16.5	98.5%	0.63	86.5	10.50	Oxide	1.5m @ 1.26g/t Au & 81.4% CN Rec 3m @ 1.77g/t Au & 92.3% CN Rec			1.5m @ 1.26g/t Au & 81.4% CN Rec 3m @ 1.77g/t Au & 92.3% CN Rec						FA	
RR25-04	163.1	1.5	1.5	98.5%	0.22	73.4	0.33	Oxide											FA
RR25-04	230.1	6.1	6.0	98.6%	0.28	59.5	1.68	Oxide											FA
RR25-05	288.0	12.2	11.4	93.4%	0.34	64.4	4.14	Oxide	3m @ 0.56g/t Au & 78.2% CN Rec										FA
RR25-05	321.6	38.1	35.5	93.1%	0.80	88.3	30.44	Oxide	4.6m @ 1.99g/t Au & 103.6% CN Rec 10.7m @ 1.14g/t Au & 92.3% CN Rec 7.6m @ 0.75g/t Au & 74.8% CN Rec			4.6m @ 1.99g/t Au & 103.6% CN Rec 1.5m @ 5.15g/t Au & 55.1% CN Rec 1.5m @ 1.27g/t Au & 19.7% CN Rec			1.5m @ 2.83g/t Au & 96.1% CN Rec 1.5m @ 5.15g/t Au & 55.1% CN Rec			FA	
RR25-06	304.8	1.5	1.4	93.0%	0.92	18.6	1.40	Sulphide											FA
RR25-06	306.3	21.3	19.8	93.0%	0.76	77.7	16.26	Oxide	10.7m @ 1.08g/t Au & 85.8% CN Rec			4.6m @ 1.65g/t Au & 89.3% CN Rec						FA	

									1.5m @ 1.26g/t Au & 100.4% CN Rec	1.5m @ 1.26g/t Au & 100.4% CN Rec	
RR25-06	333.8	15.2	14.2	93.1%	0.62	61.4	9.48	Oxide	13.7m @ 0.66g/t Au & 60% CN Rec	1.5m @ 1.19g/t Au & 95% CN Rec 1.5m @ 1.46g/t Au & 53.4% CN Rec	FA
RR25-08	239.3	3.0	2.7	89.1%	0.41	57.4	1.24	Oxide	1.5m @ 0.51g/t Au & 58.4% CN Rec		FA
RR25-08	254.5	1.5	1.3	88.3%	0.26	45.8	0.40	Oxide			FA
RR25-09	137.2	12.2	10.7	87.8%	0.20	83.2	2.39	Oxide			FA
RR25-09	254.5	1.5	1.3	86.4%	0.54	2.8	0.82	Sulphide			FA
RR25-10	112.8	7.6	7.3	96.3%	0.32	78.2	2.41	Oxide	1.5m @ 0.58g/t Au & 99% CN Rec		FA
RR25-10	144.8	4.6	4.4	96.6%	0.24	73.1	1.07	Oxide			FA
RR25-12	114.3	3.0	2.6	85.7%	0.74	9.4	2.24	Sulphide			FA
RR25-12	117.3	7.6	6.5	85.7%	0.26	78.3	1.99	Oxide			FA
RR25-13	18.3	3.0	3.0	98.1%	0.31	78.0	0.96	Oxide			FA
RR25-13	228.6	35.1	34.4	98.1%	0.61	79.7	21.47	Oxide	15.2m @ 0.93g/t Au & 83.6% CN Rec 1.5m @ 0.58g/t Au & 88.1% CN Rec	1.5m @ 1.06g/t Au & 87.2% CN Rec 3m @ 2.12g/t Au & 92.9% CN Rec	1.5m @ 2.43g/t Au & 98.8% CN Rec

Table 2: SCC Drill Hole Collars

HOLE-ID	Easting	Northing	Elevation	Azimuth	Dip	Depth (m)
BW25-01	586688.7	4466415.3	2247.9	302.0	-55.00	152.4
BW25-02	586740.3	4466615.4	2228.2	220.0	-50.00	152.4
BW25-03	586573.4	4466810.4	2179.6	120.0	-69.00	243.8
BW25-04	586631.3	4466891.2	2189.3	96.0	-75.00	221.0
BW25-05	586453.0	4466937.4	2182.4	80.0	-64.00	304.8
BW25-06	586363.7	4467002.0	2186.4	270.0	-55.00	201.2
BW25-07	586313.3	4467119.3	2188.5	285.0	-59.00	152.4
BW25-08	586424.0	4467074.8	2208.5	90.0	-54.00	198.1
BW25-09	586579.0	4467125.8	2217.5	270.0	-60.00	182.9
BW25-10	586512.9	4467407.8	2192.6	130.0	-50.00	152.4
BW25-11	586376.6	4467488.3	2171.7	255.0	-60.00	249.9
BW25-14	586135.6	4466763.6	2163.9	60.0	-50.00	214.9
DS25-01	588262.1	4480059.3	1988.0	270.0	-61.00	182.9
DS25-01A	588197.1	4480060.1	1859.6	270.0	-61.00	151.5
DS25-02	588247.2	4480104.2	1991.0	273.0	-64.00	320.0
DS25-03	588257.0	4479935.9	1983.4	286.0	-60.00	336.8
DSC25-02	588257.0	4479935.9	1983.3	255.0	-60.00	260.6
DSC25-03	588389.2	4480022.3	1965.8	270.0	-60.00	487.7
DSC25-04	588343.9	4479938.4	1971.4	274.0	-60.00	446.8
DSC25-05	588262.1	4480059.3	1988.0	270.0	-64.00	336.5
GEC25-01	583007.2	4484375.3	2228.2	130.0	-46.00	611.7
JW25-01	584827.5	4473587.1	2336.6	90.0	-48.00	161.5
JW25-02	584818.6	4473487.4	2353.1	90.0	-75.00	213.4
JW25-03	584928.5	4473496.7	2372.8	90.0	-90.00	112.8
JW25-04	584788.8	4473406.4	2368.5	90.0	-50.00	184.4
JW25-05	584691.5	4473150.5	2369.3	90.0	-56.00	185.9
JW25-06	584619.9	4472892.0	2316.2	90.0	-52.00	152.4
JW25-07	584714.1	4472879.4	2307.4	90.0	-50.00	205.7
JW25-08	584803.1	4472945.4	2320.4	90.0	-65.00	152.4
JW25-09	584878.5	4472950.8	2323.8	90.0	-65.00	141.7
JW25-10	584867.5	4472848.6	2303.9	90.0	-53.00	115.8
JW25-11	584891.0	4472543.2	2287.1	90.0	-65.00	103.6
JW25-12	585045.3	4472547.1	2337.5	90.0	-65.00	115.8
JW25-13	585018.9	4472452.6	2323.7	270.0	-65.00	137.2
PAL25-01	585509.4	4467121.4	2167.9	270.0	-60.00	216.4
PAL25-01A	585509.5	4467121.5	2167.9	270.0	-50.00	181.4
PAL25-02	585485.3	4467026.0	2165.0	235.0	-70.00	249.9
PAL25-04	585759.4	4467276.0	2136.4	270.0	-60.00	152.4
PR25-01	584907.2	4479802.5	2253.1	232.0	-64.00	295.7
PR25-02	585119.9	4479573.4	2203.2	230.0	-65.00	350.5

PR25-04	585121.5	4479573.0	2203.2	203.0	-64.00	320.0
PR25-05	585119.4	4479573.4	2203.3	260.0	-55.00	304.8
PR25-06	584905.6	4479800.8	2253.1	218.0	-53.00	274.3
PR25-07	584906.3	4479802.8	2253.1	254.0	-55.00	228.6
PR25-09	584643.0	4480549.0	2179.0	0.0	-90.00	274.3
RBN25-01	585114.2	4471431.8	2116.9	60.0	-60.00	152.4
RBN25-02	585275.0	4471331.8	2134.1	55.0	-60.00	152.4
RBN25-03	585427.0	4471225.8	2171.9	60.0	-62.00	152.4
RR25-01	583969.7	4486852.0	2340.0	200.0	-55.00	350.5
RR25-02	584488.8	4486902.5	2112.8	270.0	-55.00	198.1
RR25-03	583965.9	4486848.0	2340.0	205.0	-70.00	335.3
RR25-04	584172.7	4486899.0	2251.0	180.0	-50.00	304.8
RR25-05	583736.0	4486913.0	2413.5	255.0	-75.00	403.9
RR25-06	583736.4	4486914.0	2413.5	153.0	-75.00	349.0
RR25-07	584496.0	4486997.0	2092.6	270.0	-55.00	149.4
RR25-08	584685.1	4486730.4	2153.7	280.0	-80.00	275.8
RR25-09	584663.2	4486530.1	2163.2	290.0	-70.00	257.6
RR25-10	584664.6	4486529.7	2163.1	230.0	-55.00	281.9
RR25-11	584631.7	4486664.9	2188.4	245.0	-55.00	262.1
RR25-12	584657.0	4487161.3	2060.1	260.0	-55.00	144.8
RR25-13	583970.3	4486850.4	2340.0	227.0	-70.00	304.8